




Minimum Preservative Retention* Requirements

	 <small>PRESERVED WOOD PRODUCTS</small> Alkaline Copper Quaternary	 Micronized Copper Quaternary	 Micronized Copper Azole
Service Conditions	Retention Levels (pcf)		
Above Ground - General Use	0.20	0.15	0.06
Ground Contact & Fresh Water - General Use	0.40	0.34	0.15
Ground Contact - Critical Structures Foundation Use	0.60	0.60	0.23
Attributes			
Lifetime Limited Warranty**	Yes	Yes	Yes
EPA Registered	Yes	Yes	Yes
ICC-ES Evaluation Report***	ESR-1980	ESR-1980	ESR-2240

*Retention is expressed in pounds of preservative per cubic foot (kilograms per cubic meter) of wood.

**See Warranty for details.

***Refer to ICC-ES Report for additional information and for approved wood species.